

FUGRO TECHNICAL SERVICES LIMITED

MateriaLab Division,
Fugro Development Centre,
5 Lok Yi Street, 17 M.S. Castle Peak Road,
Tai Lam, Tuen Mun, N.T., Hong Kong.

Tel : +852-2450 8233
Fax : +852-2450 6138
E-mail : matlab@fugro.com.hk
Website : www.fugro.com

MateriaLab

Report No. : 061528RM60080(13)

Page 1 of 3

REPORT ON SORPTIVITY OF CONCRETE

INFORMATION SUPPLIED BY CLIENT

Client : Bestford International Ltd.

Project : Test on Waterproofing Material

Client's Ref. : --

Date casting : 07-Jul-2006

Place of Sampling : Concrete Laboratory of MateriaLab

LABORATORY INFORMATION

Date received : 24-Jun-2006

Date of test : 04-Aug-2006



Age at Test : 28 days

Sample description : Zhonghe 2000 Efficiency 2000 Waterproofing Materials

Test method used : PSSEC 16 Appendix 16.4

TEST RESULTS

Client sample ID	Laboratory sample ID	Sample dimension	Sorptivity (determined gradient from the graph of i vs $t^{0.5}$)
--	RM60080/9A	Ø74.7mmx100mm height	0.05 mm/min^{0.5}



Remark : 1. Lab batch ID : RM60080/B

Checked By : *[Signature]*

Date : 9/9/06

Certified By : *[Signature]*

Date : 12/9/2006

(Felix Chan / T.K. Cheung)

FUGRO TECHNICAL SERVICES LIMITED

MaterialLab Division,
Fugro Development Centre,
5 Lok Yi Street, 17 M.S. Castle Peak Road,
Tai Lam, Tuen Mun, N.T., Hong Kong.

Tel : +852-2450 8233
Fax : +852-2450 6138
E-mail : matlab@fugro.com.hk
Website : www.fugro.com

MaterialLab

Report No. : 061528RM60080(13)

Page 3 of 3

REPORT ON SORPTIVITY OF CONCRETE

INFORMATION SUPPLIED BY CLIENT

Client : Bestford International Ltd.

Project : Test on Waterproofing Material

Client's Ref. : --

Date casting : 07-Jul-2006

Place of Sampling : Concrete Laboratory of MaterialLab

LABORATORY INFORMATION

Date received : 24-Jun-2006

Date of test : 04-Aug-2006



Age at Test : 28 days

Sample description : Zhonghe 2000 Efficiency 2000 Waterproofing Materials

Test method used : PSSEC 16 Appendix 16.4

TEST RESULTS

Client sample ID	Laboratory sample ID	Sample dimension	Sorptivity (determined gradient from the graph of i vs $t^{0.5}$)
--	RM60080/9C	Ø74.7mmx100mm height	0.05 mm/min^{0.5}



Remark : 1. Lab batch ID : RM60080/B

Checked By : [Signature] Date : 9/9/06 Certified By : [Signature] Date : 12/9/2006
(Felix Chan / T.K. Cheung)